

In the Claims

Claims 1-30 (Canceled)

31. (Currently amended) A method for repair of ~~damaged, injured, diseased or aged articular cartilage and cartilage~~ lesions, said method comprising steps:

a) preparing a porous support matrix containing a plurality of pores having a pore size from about 50 to about 500 μm , wherein said matrix is prepared as a porous sponge, porous scaffold, porous honeycomb or porous honeycomb-like lattice;

b) seeding said support matrix with chondrocytes isolated from a donor and suspended in a collagenous solution or collagenous gel;

c) applying a constant or cyclic hydrostatic pressure to ~~a construct comprising the support matrix of step (a)~~ seeded with chondrocytes ~~from step (b)~~ ~~suspension of step (b)~~ for a period from about one hour to about 30 days followed by a resting period at a static atmospheric pressure for about one day to about 60 days,

wherein said hydrostatic pressure is from about 0.01 MPa to about 10 MPa above atmospheric pressure ~~and is applied at from about 0.01 to about 2.0 Hz;~~

d) pre-treating a cartilage lesion by depositing a layer of a biologically acceptable bottom sealant into said lesion before implanting said seeded support matrix construct therein;

e) implanting said seeded support matrix construct into said pre-treated lesion of step d); and

f) depositing a layer of a biologically acceptable top sealant over said seeded support matrix construct implanted into said lesion.

32. (Previously presented) The method of claim 31 wherein said top and said bottom sealants are the same or different.

33. (Currently amended) The method of claim 32 wherein said top or bottom sealant is selected from the group consisting of gelatin; a copolymer of polyethylene glycol and poly-lactide; a copolymer of polyethylene glycol and poly-glycolide; periodate-oxidized gelatin; polyethylene glycol diacrylate derivatized with 4-armed pentaerythritol thiol; polyethylene glycol derivatized with 4-armed tetra-succinimidyl ester; polyethylene glycol derivatized with tetra-thiol; polyethylene glycol-co-poly(α -hydroxy acid) diacrylate macromer; 4-armed polyethylene glycol derivatized with succinimidyl ester and thiol cross-linked with methylated collagen, derivatized polyethylene glycol cross-linked with alkylated collagen, derivatized polyethylene glycol cross-linked with methylated collagen, derivatized polyethylene glycol with tetra-hydrosuccinimidyl; and derivatized polyethylene glycol with tetra-thiol; and a combination thereof.

34. (Previously presented) The method of claim 33 wherein said sealant is derivatized polyethylene glycol cross-linked with alkylated collagen wherein the alkylated collagen is methylated collagen.

35. (Previously presented) The method of claim 34 wherein the support matrix is prepared from a material selected from the group consisting of Type I collagen; Type II collagen; Type IV collagen; cell-contracted collagen containing material selected from the group

consisting of proteoglycan, glycosaminoglycan and glycoprotein; gelatin; agarose; hyaluronin; fibronectin; laminin; bioactive peptide growth factor; cytokine; elastin; fibrin; polymeric fiber made of a polylactic acid; polymeric fiber made of a polyglycolic acid; polycaprolactone; polyamino acid; a polypeptide, and collagenous gel; a copolymer thereof and a combination thereof.

36. (Currently amended) The method of claim 35 wherein said ~~support matrix is the Type I or Type II collagen~~ porous sponge, porous honeycomb, porous scaffold or a porous honeycomb-like lattice is prepared from a material selected from the group consisting of Type I collagen and Type II collagen.

37. (Previously presented) The method of claim 36 wherein said hydrostatic pressure is the cyclic hydrostatic pressure from about 0.5 MPa to about 5 MPa applied at frequency from about 0.5 Hz.

38. (Previously presented) The method of claims 35 wherein said cyclic hydrostatic pressure is about 3.0 MPa applied at frequency of about 0.5 Hz and is applied for from about seven days to about 14 days and wherein said resting period is from about seven to about 28 days.

39. (Currently amended) The method of claim 38 wherein ~~said construct comprising~~ said support matrix seeded with chondrocytes is submitted to the cyclic hydrostatic pressure and subjected to a flow of culture media at a flow rate from about 1 $\mu\text{L}/\text{min}$ to about 500 $\mu\text{L}/\text{min}$.

40. (Previously amended) The method of claim 39 wherein said flow rate is about 5 $\mu\text{L}/\text{min}$ to about 50 $\mu\text{L}/\text{min}$ and is performed in the presence of about 1% to about 20% oxygen.

41. (Currently amended) The method of claim 40 wherein ~~a combination of said construct deposited into said lesion and said top sealant is the~~ derivatized polyethylene glycol cross-linked with methylated collagen and ~~top sealant deposited over said construct~~ results in an outgrowth of a layer of squamous-like flattened superficial zone chondrocytes ~~(superficial cartilage layer)~~ covering the ~~layer of the second~~ top sealant and overgrowing the cartilage lesion.

42. (Previously amended) The method of claim 35 wherein said collagenous gel is a polymeric thermoreversible gelling hydrogel.

43. (New) The method fo claim 31 wherein said pressure is applied at from about 0.01 to about 2.0 Hz.